

## SUSONITY KNOWLEDGE HUB



### Styling Impulse: After Hour

#### STYLING FORMULA

Technology: 2-Layer coating

Basecoat layer pigmentation:

Colorstream® F20-52 SW Mineral Red	61,5%
Xirallic® T260-23 SW Tigris Blue	11,5%
Heliogen Blue L7101F	19,2%
Hostaperm Red Violet ER 02	7,7%
<b>Pigmentation</b>	<b>100%</b>

**Total PWC:** 26,0%

#### TECHNICAL DATA

##### Base Coat

1-component water-borne basecoat  
applied layer thickness: 14 – 18 µm

##### Clear Coat

2K high gloss clear coat  
applied layer thickness 35 – 45 µm

##### Pigmentation

Given in % and as total PWC.  
The PWC (Pigment Weight Concentration) in dry film is indicated as  
$$PWC = p / (p + b)$$

p = total weight pigments (solid)

b = weight binder (solid)

In the dry state: Pigment / binder ratio =  $(\Sigma \text{Pigment}) / (\text{Total solid content (wet form)} - (\Sigma \text{Pigment}))$

#### Feasibility for on-line application

Stylings in our Styling Impulse are intended to demonstrate effect color directions and possibilities. Although we have tried to make the formulations as realistic as possible, we cannot guarantee their full feasibility for on-line application. A certain degree of modification and fine tuning will probably be necessary.

#### THIRD PARTY TRADEMARKS

Irgazine® is a registered trademark of BASF SE, Ludwigshafen, Germany

Hostaperm® is a registered trademark of Clariant